

VALIANT

Lacquer Primer Surfacer



DESCRIPTION:

A premium quality lacquer-type primer that provides a solid foundation for lacquer topcoat.

RECOMMENDED USES:

Interior wood and metal surfaces.

PRODUCT APPEARANCE	: Liquid
PACKAGE VISCOSITY	: 130-135 kus
DRY FILM THICKNESS	:
DRY SET TO TOUCH	: 10 minutes
DRY HARD	: 1 hour
COATING INTERVAL	: 1 hour
THINNING	: Reduce with Lacquer Thinner
APPLICATION	: spray
COVERAGE	: 20-25 m ² /4L depending on surface porosity & texture
CLEAN-UP	: Lacquer Thinner
PACKAGING SIZE	: 1, 4 liters
AVAILABLE COLORS	: White V-100

SURFACE PREPARATION:

Wood

New or unpainted surface

Use kiln-dried wood with a maximum moisture content of 12%. Sand wood until smooth. Counter sink nail heads then putty. Dust the surface and wipe clean.

Old or previously painted or stained surface

Remove all loose, peeling, chalking or blistering paint, dirt, dust, grease, oil, and other contaminants by scraping. Sand the surface. Dust the surface and wipe clean.

Metal

New or unpainted surface

Ensure that the metal surface is free from oil, grease, rust, and other surface contaminants. Remove thick rust by sand blasting and thin rust by wire brushing, sanding or scraping. Dust the surface and wipe surface clean prior to priming with metal primer red oxide.

Old or previously painted surface

Remove all loose, peeling, paint, rust, dirt, dust, grease, oil and other contaminants by wire brushing or scraping. Wipe surface clean and priming with metal primer red oxide.

APPLICATION:

Do not thin. Inter-mix all cans of same color to ensure color uniformity and consistency. Always stir paint before and occasionally during application. Apply only when temperature is from 10° – 35°C. Do not paint in rain or rain imminent weather. For best results always use high quality roller and brush.

VALIANT

Lacquer Primer Surfacer



PAINTING DIRECTIONS: For best results use:

Wood

1st coat: Valiant Lacquer Primer Surfacer White V-100. Allow 1 hour drying time.

To remedy surface imperfections:

Putty: Valiant Lacquer Spot Putty V-200. Allow 1 hour drying time then sand.

Spot prime: Valiant Lacquer Primer Surfacer White V-100. Allow 1 hour drying time.

2nd – 3rd coats: Valiant Automotive Lacquer Enamel of desired color.
Allow 1 hour drying time between coats.

Metal

1st coat: Universal Professional MetalPro Epoxy Primer White

To remedy surface imperfections:

Putty: Valiant Lacquer Spot Putty V-200. Allow 1 hour drying time then sand.

Spot prime: Valiant Lacquer Primer Surfacer White V-100. Allow 1 hour drying time.

2nd – 3rd coats: Valiant Automotive Lacquer Enamel of desired color.
Allow 1 hour drying time between coats.